

CLAIMS

1. A dry etching method comprising etching a metallic surface selected from copper, silver, gold, or an alloy containing as a main component at least one of these metals by plasma of an etching gas containing at least nitrogen oxide while being reacted with the plasma.
2. A dry etching method as claimed in Claim 1, wherein the etching gas is a mixed gas of nitrogen oxide and hydrogen, or a compound containing hydrogen.
3. A dry etching method as claimed in Claim 2, wherein the compound containing hydrogen is one or two or more selected from the group consisting of ammonia, a hydrocarbon, a halogen-containing hydrocarbon, and hydrogen sulfide.
4. A dry etching method as claimed in one of Claims 1 to 3, wherein a mask material covering the metallic surface on etching is one selected from the group consisting of titanium, a titanium alloy, aluminum, and an aluminum alloy.

Add
A2